

# EA28150

Copolymer of Ethylene vinyl acetate

## General

<b>Additive</b>	<ul style="list-style-type: none"> <li>• Anti-Oxidant</li> <li>• Anti-agglomerate</li> </ul>
<b>Application</b>	<ul style="list-style-type: none"> <li>• Hot Melt Adhesive</li> </ul>

## Properties

Item	Typical Value	Test Based on
Density @ 23°C	0.946g/cm <sup>3</sup>	ASTM D1505
Melt Flow Rate, 2.16KG	150g/10min	ASTM D1238
Vinyl Acetate Content	28wt%	LG Method
Melting Point, DSC	70°C	LG Method
Tensile Strength@Break	40kg/cm <sup>2</sup>	ASTM D638
Elongation@Break	900%	ASTM D638
Hardness, Shore A	74	ASTM D2240
Softening Point, Vicat	<40°C	ASTM D1525

※ The data and information represented are intended as a general guide only and are not construed as specification limits.

## Performance

- Uniform VA content and MI
- Products line with various VA contents and MI
- Excellent compatibility with other raw materials of HMA
- Good organoleptic property